



# TARA PAINTS & CHEMICALS

(An ISO 9001:2015, 18001:2007 Certified Company)

## India

A/423/4, Mahagujrat Industrial Estate, Sarkhej Bavla Rd, NH 8A, Village, Moraiya, Gujarat 382213, INDIA  
Customer care : +91 8000011774, email : [customercare@tarapaints.com](mailto:customercare@tarapaints.com), web: [www.taralac.com](http://www.taralac.com)

## North America

3106- A, Bethel Road , Upper Chichester – PA 19061  
OFFICE : 484 474 0278 EMAIL : [karan@tarapaints.com](mailto:karan@tarapaints.com)

## 2310 Epoxy FC Hardener - WW [2:1]

It is an Amino Polyamide hardener used in conjunction with Epoxy base coating for curing purpose.

### Technical Data

<b>Weight per Liter at 30°C</b>	1.0 ± 0.1 kg
<b>Thinner</b>	Taralac Epoxy Thinner, Thinner – 555,Thinner - 111
<b>Solids</b>	98 % Min.
<b>Appearance</b>	W.W.Clear to sl.Pale Yellow

### Health and Safety Information

<b>Flash Point</b>	Non Flammable
<b>Fire Hazard Class</b>	Flammable
<b>Health Hazard Class</b>	Harmful as it contains volatile organic solvents. Avoid contact with skin and eyes.
<b>Safety Precautions</b>	Work in a well-ventilated place. Protective clothing, such as overalls, hand gloves and eye goggles, are recommended.
<b>Storage and Handling</b>	Store in a cool dry place.
<b>Disposal</b>	Dispose in land filling. Do not dispose in any drain or water channel.

#### Note:

Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with Thinner. Once units of Paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units.

Surface temperature must always be a minimum of 3°C (5°F) above dew point.  
Ensure adequate ventilation. Condensation occurring during or immediately after application may result in a matt finish and an inferior film.